

Cork ACN 60 Plus

Fuel, Oil, Gas and Transformer Gaskets

ASTM Spec D1170	<i>Unavailable</i>
ASTM Spec F104	<i>F225000</i>
Binder	<i>Nitrile</i>
Cork Granule Size (mm)	<i>0.5/1</i>
Colour	<i>Natural</i>
Density (kg/m³)	<i>750-900</i>
Hardness, Shore A	<i>70-80</i>
Compressibility at 2.76 MPa	<i>20-30</i>
Recovery after (%)	<i>>80</i>
Tensile Strength (kPa)	<i>>2400</i>
Flexibility – Original (F5)	<i>No Cracks</i>
Flex – ASTM Oil No1 70h @ 100C (F16)	<i>No Cracks</i>
Flexibility – Oven aged 70 h @ 100C (F1)	<i>No Cracks</i>
Volume Change After Immersion	
ASTM No1 Oil, 70h @ 100C (%)	<i>-10 to +10</i>
ASTM No3 Oil, 70h @ 100C (%)	<i>-5 to +15</i>
ASTM Fuel A, 22h @ 23C (%)	<i>-2 to +10</i>

For sales and technical advice, please contact:

*Tel: +61 08 9251 1600 or Toll Free No.1300 79 82 79 (in Australia),
Fax: +61 08 93509286
Email: sales@klinger.com.au or technical_service@klinger.com.au
Website: www.klinger.com.au*

Subject to technical alternations

...Sealing with Security